

PRODUCT DATA

PEGARUST

DESCRIPTION

Solvent-based rust preventing coating containing high polymers.

MAIN PROPERTIES

Waterproof - flexible and elastic - contains neither lead compounds nor zinc chromate - very durable - excellent resistance against chemical agents in atmosphere - dries even in humid weather conditions - excellent substrate wetting - adheres even on moist substrates - can be applied in thick layers.

RECOMMENDED USES

On iron, galvanised steel, aluminium, zinc, etc.

TECHNICAL DATA

Appearance:	Glossy (gloss 60°: ± 70%)
Colour:	Grey green, beige grey, red
Density:	Approx. 1,15 g/cm ³
Solids Content:	In volume: 46 ± 2% In weight: 55 ± 2%
Recommended film thickness:	Wet film: ± 345 micron (cons.: 2,9 m ² /l) Dry film: ± 160 micron (cons.: 2,9 m ² /l)
Flashpoint:	28°C
VOC-content:	500 g/l max.
Ready-for-use mixture:	500 g/l max.
Category:	A/i
EU Limit values:	600 g/l (2007) / 500 g/l (2010)

Drying times 20°C/50% r.h.
To recoat: 24 - 48 hours
Full hardness: ± 1 week

Coverage

Theoretical: ± 2,9 m²/l per coat (it is recommended to apply 2 coats).
Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Degrease if necessary. Derust substrate according to the conventional derusting techniques (sandblasting Sa2 and mechanical sanding St3). On a humid substrate, apply the first coat by brush or roller.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush: Apply undiluted.
Roller: Apply undiluted.
Air-atomised spray: Not advisable.
Airless spray: Nozzle: 018 - 021 / Pressure: 200 - 220 bars. Apply undiluted.
Cleanup: Thinner 22

Rust-Oleum Netherlands B.V.
Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info@rust-oleum.eu
www.rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S
11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)1 30 40 00 44
F +33 (0)1 30 40 99 80
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Rotterdam House
116 Quayside
Newcastle
NE1 3DY
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info@rust-oleum.eu
www.rust-oleum.eu

PRODUCT DATA

PEGARUST

APPLICATION CONDITIONS

May be applied in humid weather conditions. Minimum ambient temperature: -5°C.

REMARKS

On new galvanised surfaces and new zinc apply first a coat of Pegacryl Metal Primer.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.
Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info@rust-oleum.eu
www.rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S
11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)1 30 40 00 44
F +33 (0)1 30 40 99 80
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Rotterdam House
116 Quayside
Newcastle
NE1 3DY
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info@rust-oleum.eu
www.rust-oleum.eu